AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1 - 4. (canceled).

5. (currently amended): An~~The~~ interlayer film for a laminated glass, which contains a polyvinyl acetal resin and a moisture resistance improver, ~~according to Claim 1,~~

wherein the moisture resistance improver is trimethyl phosphate, triethyl phosphate, tributyl phosphate, tris(2-chloroethyl) phosphate, triphenyl phosphate, tricresylphosphate, cresyl diphenylphosphate, di-2-ethylhexyl phosphate, methyl acid phosphate, ethyl acid phosphate, proyl acid phosphate, isopropyl acid phosphate, butyl acid phosphate, lauryl acid phosphate, stearyl acid phosphate, 2-ethylhexyl acid phosphate, isodecyl acid phosphate, phenylphosphonic acid, poly(oxyethylene) octylephenyl ether phosphate ester, phosphate ester, poly(oxyethylene) nonylphenyl ether phosphate ester or poly(oxyethylene) laurylphenyl ether phosphate ester ~~a phosphate ester compound~~.

6. (currently amended): The interlayer film for a laminated glass according to Claim ~~1~~5, which contains a chelating agent and/or a compound having at least one carboxyl group.

7. (original): The interlayer film for a laminated glass according to Claim 6, wherein the chelating agent is acetylacetone.

8. (original): The interlayer film for a laminated glass according to Claim 6,

wherein the compound having at least one carboxyl group is 2-ethyl hexanoic acid.

9. (currently amended): The interlayer film for a laminated glass according to Claim ~~1~~5,

which contains a heat ray shielding particle.

10. (original): The interlayer film for a laminated glass according to Claim 9,

wherein the heat ray shielding particle is at least one kind selected from the group consisting of a tin-doped indium oxide (ITO) fine particle, an antimony-doped tin oxide (ATO) fine particle, an aluminum-doped zinc oxide (AZO) fine particle, an indium-doped zinc oxide (IZO) fine particle, a silicon-doped zinc oxide fine particle, a zinc antimonic anhydride fine particle, and a lanthanum hexaboride fine particle.

11. (canceled).

12. (currently amended): A laminated glass,

which is obtainable by using the interlayer film for a laminated glass according to Claim ~~1~~5.

13. (previously presented): The interlayer film for a laminated glass according to Claim 2,

wherein the moisture resistance improver has a solubility parameter in the range of 10.0 to 20.0 $(cal/cm^3)^{1/2}$.

14. (previously presented): The interlayer film for a laminated glass according to Claim 2,

wherein the moisture resistance improver has a relative permittivity in the range of 20 to 35 at 25°C.

15. (previously presented): The interlayer film for a laminated glass according to Claim 3,

wherein the moisture resistance improver has a relative permittivity in the range of 20 to 35 at 25°C.

16. (previously presented): The interlayer film for a laminated glass according to Claim 2,

wherein the moisture resistance improver is a phosphate ester compound.

17. (previously presented): The interlayer film for a laminated glass according to Claim 3,

wherein the moisture resistance improver is a phosphate ester compound.

18. (previously presented): The interlayer film for a laminated glass according to Claim 4,

wherein the moisture resistance improver is a phosphate ester compound.

19. (previously presented): The interlayer film for a laminated glass according to Claim 2,

which contains a chelating agent and/or a compound having at least one carboxyl group.

20. (previously presented): The interlayer film for a laminated glass according to Claim 3,

which contains a chelating agent and/or a compound having at least one carboxyl group.